

試験報告書

依頼者 Dacian Technology Material Co., Ltd 殿
品名 マスク 1点
試験項目 バクテリア飛沫捕集(ろ過)効率(BFE)他

平成29年11月14日付けで当所に提出された試料の
試験結果は、下記のとおりです。

平成29年11月17日

カケン

〒550-0002 大阪市西区江戸堀2丁目5番19号
一般財団法人 **カケンテストセンター**
大阪事業所 生物ラボ
Tel (06)-6441-0399 Fax (06)-6441-6803



記

試験結果

1. マスクの人工血液バリア性

試料 ^{*2}		圧力 ^{*1}		
		10.6kPa (80mmHg)	16.0kPa (120mmHg)	21.3kPa (160mmHg)
dc face mask	1	○	○	○
	2	○	○	○
	3	○	○	○
	4	○	○	○
	5	○	○	○

注^{*1} ○:浸透なし ×:浸透あり

^{*2} 依頼者の指示により、測定回数を5回とした。

2. BFE

試料	バクテリア飛沫捕集(ろ過)効率(%)			
	No.1	No.2	No.3	平均
dc face mask	99.8	99.9	99.9	99.9

3. 圧力損失

試料	圧力損失 (mmH ₂ O/cm ²)					平均
	No.1	No.2	No.3	No.4	No.5	
dc face mask	3.8	4.3	4.4	5.0	4.2	4.3

試験方法

マスクの人工血液バリア性:ASTM F1862 (ISO 22609)

バクテリア飛沫捕集(ろ過)効率(BFE)試験:ASTM F2101-14

供試菌:黄色ぶどう球菌・*Staphylococcus aureus* ATCC 6538

圧力損失:MIL-M-36954C

KAKEN**Kaken Test Center GENERAL INCORPORATED FOUNDATION**2-5-19, Edobori, Nishi-ku, Osaka,550-0002/ Japan
Tel: +81-(0)6-6441-0399, Fax: +81-(0)6-6441-6803

Kaken Test Center is formerly named as "Japan Synthetic Textile Inspection Institute Foundation(JSTIIF)".

No.1/2

Test report No. : OS-17-052767-6

Date : November 17 , 2017

TEST REPORTRequested : Dacian Technology Material Co., Ltd
Test sample : Face mask 1 sample
Test items : Bacterial Filtration Efficiency (BFE) and others
Received : November 14, 2017**This is to report that the results of laboratory test applied on the sample are as follows:****1. Test result****1.1. Resistance to penetration by synthetic blood**

Test Sample *		Pressure		
		10.6kPa (80mmHg)	16.0kPa (120mmHg)	21.3kPa (160mmHg)
dc face mask	1	Pass	Pass	Pass
	2	Pass	Pass	Pass
	3	Pass	Pass	Pass
	4	Pass	Pass	Pass
	5	Pass	Pass	Pass

*The number of measurements was set to five times by the client.

1.2. Bacterial Filtration Efficiency (BFE)

Test sample	BFE (%)			
	No.1	No.2	No.3	Average
dc face mask	99.8	99.9	99.9	99.9

(To be continued on No.2/2)

Kaken Test CenterGENERAL INCORPORATED FOUNDATION
Lab Address: 2-5-19, Edobori, Nishi-ku, Osaka,
550-0002/ Japan
Tel: +81-(0)6-6441-0399
Fax: +81-(0)6-6441-6803

Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted.

KAKEN

Kaken Test Center GENERAL INCORPORATED FOUNDATION

2-5-19, Edobori, Nishi-ku, Osaka, 550-0002/ Japan
Tel: +81-(0)6-6441-0399, Fax: +81-(0)6-6441-6803

No.2/2

Test report No. : OS-17-052767-6

Date : November 17 , 2017

TEST REPORT

(Continued from No.1/2)

1.3. Differential pressure

Test Sample	Differential pressure (mmH ₂ O/cm ²)					
	No.1	No.2	No.3	No.4	No.5	Average
dc face mask	3.8	4.3	4.4	5.0	4.2	4.3

2. Test method: Resistance to penetration by synthetic blood : ASTM F1862 (ISO 22609)
Bacterial Filtration Efficiency (BFE) : ASTM F 2101-14
Test Bacteria : *Staphylococcus aureus* ATCC 6538
Differential pressure : MIL-M-36954C

3. Sample:

(EN KAKEN K)

Kaken Test Center General Incorporated Foundation
Osaka Laboratories
Biological Laboratory

Inspector : 中曾根 吾明
T. Nakasone

Period.